



TECHNICAL INFORMATION SHEET

Uneeke™ Kynar 500®/Hylar 5000® Pre-Finished Galvalume® Steel Architectural Sheet & Coil

Item Description: 24 gauge

Product Information

Description:

Uneeke PVDF (polyvinylidene fluoride) Coated Galvalume® Steel Architectural Sheet & Coil is extra smooth, tension leveled, hot-dipped 55% Al-Zn coated steel that is primed and coated on one side with Uneeke full strength Hylar 5000/Kynar 500 (contains a minimum of 70% Hylar /Kynar polyvinylidene fluoride (PVDF) resins) premium fluoropolymer coating system of 1.0 (±0.1) mil total dry film thickness. For additional protection, a wash coat of 0.3 – 0.4 mil dry film thickness is applied to the reverse side. An optional strippable protection film is applied for protection during fabrication and installation. Uneeke PVDF Coated Galvalume Steel Architectural Sheet & Coil is for general sheet metal use in building applications and can be utilized for fascia panels, soffits, gravel stops, copings, and roofing such as flat seam, standing seam, batten seam, and mansards.

Method of Application:

1. Install in accordance with recognized sheet metal practices.
2. Uneeke sheets can be cut, formed, and fastened using conventional hand or power tools.
3. For best results cutting tool edges should be kept sharp, clean, properly dressed, and closely aligned.
4. Fabrication and erection can be accomplished with strippable plastic film in place. Film should be removed from areas of concealed or joined pieces.

Storage:

- Uneeke metal sheet and coil should be stored in a well ventilated, dry place where no moisture can contact them. Moisture (from rain, snow, condensation, etc.) trapped between layers of material may cause water stains or white rust, which can affect the service life of the material and will detract from its appearance.
- If outdoor storage cannot be avoided, protect the sheet and coil with a ventilated canvas or waterproof paper cover. Do not use plastic, which can cause condensation. Keep the material off the ground in an inclined position with an insulator such as wood.
- Maximum 2,000 lb of sheets per pallet.



LEED® Information:

Post-Consumer Recycled Content: 36.9%

Pre-Consumer Recycled Content: 19.8%

Kynar 500/Hylar 5000 Paint Finish: AAMA 621-02

Manufacturing Location: Anoka, MN



**NOTE: LEED® is a registered trademark of the U.S. Green Building Council*

Precautions:

- Protective film may degrade or become brittle with exposure to direct sunlight. Therefore, it must be removed immediately.
- The performance of this material in the field depends substantially on the integrity of the paint film and on the underlying coating of zinc-aluminum being intact. Therefore, this Uneeke product should not be used in areas of high abrasion or where it is subject to mechanical damage.
- Product is pre-finished material; care must be exercised during fabrication and erection to avoid surface damage.
- Uneeke recommends a minimum bend radius of 2T. Anything less than a 2T bend radius can cause crazing to the material.
- Attention should be paid to good house-keeping practices.
- Tools must be clean and properly dressed.
- Avoid dragging sheets over surfaces which may scratch or mar the finish.
- For general sheet metal use in building applications.
- Do not cut with power saws or abrasive blades.



PRODUCT DATA

Property	Value
Color	14 Standard Colors; See Current Uneeke color chart
Finish	Extra Smooth Matte, Low to Medium Gloss
Optional Finish	Extra Low Gloss*, High Gloss* and Stucco Embossed (Mechanical Finish)*
Wash Coat	Polyester
Gauge: 24 ga	Weight: 1.000/lb/ft ² , 4.89 kg/M ²
<i>Note: *May not be available in all colors, gauges, or widths. Additional lead times may apply. Contact your Uneeke Manufacturing advisor for additional information</i>	

Typical Properties of Base Material

Property	Value
Base Metal	AZ50 – Hot dipped Galvalume® (55% Aluminum and 43+ % zinc) steel sheet, commercial weight, meeting ASTM A792/A792M
Minimum Yield	50 KSI
Co-efficient of Thermal: <i>Expansion</i> <i>Modules of Elasticity Specification</i>	06.7 x 10 ⁻⁶ in/in/F (13.9m/m.Kx10 ⁻⁶) 29.0 x 10 ⁶ x KSI (200 GPa) ASTM E111-04



Typical Properties of Fluoropolymer Coating

Property	ASTM Standard	Value
Abrasion Resistance	ASTM D 968, Method A	Coefficient of sand abrasion 65± 10 Liters
Accelerated Weathering	ASTM D 4587 Condition B or ASTM G23 Method 1 or 2, type EH apparatus Hours: 5000 ASTM D 4587 Condition B or ASTM G 53, Method 1 or 2, type EH apparatus or ASTM G154 Hours: 5000 ASTM D 4587 Condition B or ASTM G23, Method 1 or 2, type EH apparatus or ASTM G151 Hours: 3000 ASTM D 3361 Hours: 1000	Chalk: Rating of 8 or better per ASTM D 4214 Color: ≤2ΔE color change per ASTM D2244 Chalk: Rating of 8 or better per ASTM D 4214 Color: ≤2ΔE color change per ASTM D2244 Chalk: Rating of 8 or better per ASTM D 4214 Color: ≤2ΔE color change per ASTM D2244 Acceptable – No cracking, peeling, blistering, loss of adhesion of the protective coating, or corrosion of the base metal Chalk: Rating of 8 or better per ASTM D 4214, Method A (ASTM D 659) Color: <5ΔE Hunter Units per ASTM D 2244
Adhesion	ASTM D 3359, Method B	No loss of adhesion
Chalk Resistance	ASTM D 659	No Chalk; Rating 9-10
Chemical/Acid Pollution Resistance	ASTM D 659	No Chalk; Rating 9-10
Cyclic Salt Fog	ASTM D 5894 Hours: 3000	Scribe: Rating of 8, 1/32" creepage from scribe per ASTM D 1654, procedure A Field: Rating of 10, no blistering per ASTM D 1654
Formability	ASTM D 522	No cracking, no loss of adhesion to point of metal rupture
Specular Gloss	ASTM D 523	25-35 at 60 degrees
Harness	ASTM D 3363	HB to 2H
Humidity Resistance	ASTM D 2247 Hours: 2000 ASTM D 1735 Hours: 1000	Rating of 10; No blistering No blistering, no loss of adhesion
Impact Resistance	ASTM D 2794	Reverse & Direct Impact: No cracking and no loss of adhesion
Salt Spray Resistance	ASTM B 117 Hours: 2000	Scribe: Rating of 7, 4 mm creepage Field: Rating of 8
Tunnel Test	ASTM E84	Class A Coating Field: Rating of 8
UV Exposure	ASTM G 154 Hours: 2016	Chalk: Rating of 8 or better per ASTM D 4214, Method A (ASTM D659) Color: <5ΔE Hunter Units per ASTM D 2244
Wet Adhesion	Water Immersion Hours: 1500	No loss of adhesion

*Kynar 500 is a registered trademark of Arkema, Inc.

*Hylar 5000 is a registered trademark of Solvay Solexis Inc.

*Galvalume is a registered trademark of Bieci International Inc.



Please contact Uneeke Technical Services Department at 801-692-2800 for further information.

This sheet is meant to highlight Uneeke products and specifications and is subject to change without notice. Uneeke takes responsibility for furnishing quality materials which meet published Uneeke product specifications or other technical documents, subject to normal roof manufacturing tolerances. Neither Uneeke nor its representatives practice architecture. Uneeke offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. Uneeke accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Uneeke representative is authorized to vary this disclaimer.